



AVM Top Coat 620-Max

Hybrid, Aliphatic, Polyurea Waterproofing Membrane Topcoat

Generic Spec

Section 071800/ 071816 / 096700 / 096713

Product Name

AVM Top Coat 620-Max

By

AVM Industries, Inc. 8245 Remmet Ave,
Canoga Park, CA 91304 888.414.1041
818.888.0050 www.avmindustries.com

Product Description

AVM Top Coat 620-Max is a heavy duty, two-component, fast setting, rapid curing, solvent free, high solids, hybrid aliphatic polyurea elastomeric membrane that provides long lasting protection to the coated surfaces. Top Coat 620 may be applied in single or multiple coats and can be installed in temperatures as low as 20°F (-7°C).

Where to Use

AVM Top Coat 620-Max is intended for use as the Top Coat for Polyurethane Pedestrian and Vehicular Deck Coating Systems. It can also be applied to properly prepared interior or exterior concrete, plywood, and metal surfaces.

Warranty

Contact AVM Industries for warranty details.

Delivery, Storage, and Handling

- Delivery of all the system materials to the job site must be in their original sealed containers and bags, with manufacturer's name and label intact.
- Handle and store containers and bags in accordance with printed instructions.
- Store at temperatures between 50°F and 90°F.
- Keep all materials out of the reach of children.
- If irritation occurs during use, liberally flush affected areas with water. If irritation continues, see a physician immediately.

Installation

Surface Preparation: Surface must be clean and dry. When installing over Aussie Membrane 520 (base coat), the base coat must be fully cured and tack free.

Mixing: Premix Part A and Part B components using a low-speed mechanical mixer until a homogeneous mixture and color is obtained (typically 3 minutes). Use care not to allow the entrapment of air into the mixture.

Application: Apply at the recommended coverage rate using a roller, notched squeegee, or trowel. When applying an aggregate coat, (sand layer) Apply the aggregate evenly at the appropriate rate into the wet coating and if desired, back-roll. (see AVM System 620 installation instructions).
AVM Top Coat 620-Max requires a continuous coating application to minimize lines and/or streaking. For proper adhesion between coats, re-coating must be done within 8-12 hours.

Curing: At 75°F (24°C) and 50% relative humidity, allow each coat to cure a minimum 30 minutes to 2 hours. Cure time will vary depending on temperature and humidity. If more than 24 hours passes between coats, reprime surface with AVM Primer 401 or Primer 420.

Allow a minimum 30 minutes to 2 hours before permitting light pedestrian traffic and at least 12 hours before heavy traffic. Cure time will vary depending on temperature and humidity.

Cleanup: All cleanup should be done in accordance with local regulations.

Limitations: Do not open until ready to use. Any off ratio mixing of the product will affect the properties, and the product may not cure. This product contains Isocyanates and Curative Material.

Maintenance

Contact AVM for Details

Availability and Cost

Contact AVM Industries or your approved applicator for pricing and availability.

Technical Services

Technical services are available by contacting our offices at: 888.414.1041 or 818.888.0050 or visit www.avmindustries.com

System Specifications

See next page.

Item	Packaging	Approx. Shipping Weights	VOC
Top Coat 620-AL (Part A & B Combined)	5 Gal Kit	56 lbs	60 g/l
Part-A (Net Contents 4 Gallons / 15.4 Liters)	5 Gal Bucket	45 lbs	60 g/l
Part-B (Net Contents 1 Gallons / 1.54 Liters)	1 Gal Bucket	11 lbs	60 g/l

Property	Results	Test Method
Specific Gravity	Side A: 1.05 ± 0.1 Side B: 0.99 ± 0.1	
Hardness	80 ± 3	ASTM D-2240 Shore A
Pot Life (min @ 75°F [24°C], 50% RH)	15 ± 5 minutes	
Tack Free Time	3-4 Hours	
Tensile Strength	2500 ± 100 pli (17.2 ± 0.7 kN/m)	ASTM D-412
Elongation	800 ± 100%	ASTM D-412
Tear	300 ± 25 pli (52.5 ± 4.4 kN/m)	ASTM D-624
Viscosity, at 75°F (24°C)	Side A: 1500-2500 cps Side B: 50-150 cps	
Total Solids by Volume	97%	ASTM D-2697
Volatile Organic Compounds	<0.49 lbs/gallon (59 gm/liter)	ASTM D-2369-81

Coverages

Item	Coverage Rate
AVM 620-AL Aliphatic @ 30 Mils	55 sqft/gal
AVM 620-AL Aliphatic @ 20 Mils	80 sqft/gal
AVM 620-AL Aliphatic @ 15 Mils	105 sqft/gal

Note: These are theoretical coverage rates and may vary depending on substrate types or if used as a topcoat over sand.

For a complete list of details in BIM (revit), CAD or PDF, please visit our website at www.avmindustries.com.

Approval(s): <https://www.avmindustries.com/approvals/>
Learn more about the detailed standards our products meet for approvals by various US or International Agencies or Code Councils

Patent(s): <https://www.avmindustries.com/patents/>
Some features of our product or assembly may be protected under one or more US or International Patent(s)

AVM Industries, Inc.

8245 Remmet Ave, Canoga Park, CA 91304

888.414.1041 818.888.0050

www.avmindustries.com Quality Waterproofing Products

